



# KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : BENTONITE

Code : K.C.BE-144

Technical Properties	
Fired M.O.R. ( Kg/Cm <sup>2</sup> )	*
Water of Plasticity ( % )	*
Fired color	*
wet	*
Water Absorption (%)	*
Yeild	*

Mineral Composition	
Dry M.O.R. ( Kg/Cm <sup>2</sup> )	*
Green M.O.R. ( Kg/Cm <sup>2</sup> )	*
Moisture (%)	*
Acide test (@20%HCL)	*
	*

Chemical analysis	
SiO2	52.20
Al2O3	17.16
Na2O	3.15
K2O	0.79
MgO	1.90
CaO	8.07
Fe2O3	5.40
TiO2	0.64
MnO	0.27
P2O5	0.17
S	0.04
L.O.I.	10.21
Total	*

<b>Remarks :</b>	
<b>Applications</b>	<b>Available Sizes</b>

Confirmed by :  
KAM CERAMICS

Date :