



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Ballclay**

Code : **K.C.BA-001**

Technical Properties	
M.O.R. (Kgf/Cm ²)	
Plasticity	
Firing Whiteness (at °C)	
Firing Shrinkage (at °C)	
Physial Form	
Packing	

Mineral Composition	

Chemical analysis	
SiO ₂	63.23
Al ₂ O ₃	20.14
Na ₂ O	0.44
K ₂ O	2.34
MgO	0.77
CaO	1.06
Fe ₂ O ₃	2.08
TiO ₂	0.31
MnO	0.03
P ₂ O ₅	0.05
SO ₃	1.51
L.O.I.	7.83
Total	99.79

Remarks : **It's not a white clay .**

MATERIAL PRICE PER KG :

RIALS

TRANSPORTING COST TO BANDAR-ABBAS
PER KG :

RIALS

Confirmed by :

KAM CERAMICS

Date :