



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Ballclay**

Code : **K.C.BA-002**

Technical Properties	
M.O.R. (Kg/Cm ²)	***
Plasticity	> 14
Firing Whiteness	Red Clay
Firing Shrinkage (at °C)	***
Physial Form	
Packing	

Mineral Composition	
Quartz	Pyrophyllite
Mica - Illite , di-Oct.	Hematite
Geothite	Kaolinite
Plagioclase	Alkali Feldspar
Rutile	

Chemical analysis	
SiO ₂	≤ 60
Al ₂ O ₃	≤ 26
Na ₂ O	3.3 - 4
K ₂ O	
MgO	≤ 1
CaO	
Fe ₂ O ₃	≤ 9
TiO ₂	1.50
MnO	***
P ₂ O ₅	***
SO ₃	***
L.O.I.	6.50
Total	***

Remarks :

**MATERIAL & TRANSPORTING COST TO BANDAR-ABBAS
PER KG :**

Confirmed by :
KAM CERAMICS

Date :