



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Ballclay**

Code : **K.C.BA-005**

Technical Properties	
Green M.O.R. (Kgf/Cm ²)	***
Dried M.O.R. (Kgf/Cm ²)	50.57
Firing Shrinkage (1190 °C)	0.10
Firing STRENGTH (1190 °C)	644.00
WATER ABSORPTION	0.01
Packing	BULK & BIG BAG

Mineral Composition	

Chemical analysis	
SiO ₂	66.03
Al ₂ O ₃	20.26
Na ₂ O	0.40
K ₂ O	1.06
MgO	0.38
CaO	0.14
Fe ₂ O ₃	2.11
TiO ₂	0.78
MnO	***
P ₂ O ₅	***
SO ₃	0.61
L.O.I.	6.71
Total	***

REMARKS : FIRED COLOR , DARK BUFF

MATERIAL , PAKING & TRANSPORTING COST TO BANDAR-ABBAS (PER KG) :

\$

Confirmed by :
KAM CERAMICS

Date :