



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **BALL CLAY**

Code : **K.C.BA-JKF003**

Technical Properties	
M.O.R. (Kg/Cm ²)	*
Plasticity (Peff.)	*
Firing Whiteness (1180 °C)	*
Firing Shrinkage (1180 °C)	*
Physial Form	*
Packing	*

Mineral Composition	

Chemical analysis	
SiO ₂	45.81
Al ₂ O ₃	33.14
Na ₂ O	1.27
K ₂ O	2.58
MgO	0.45
CaO	0.72
Fe ₂ O ₃	7.97
TiO ₂	1.41
MnO	0.08
P ₂ O ₅	*
SO ₃	*
L.O.I.	6.20
Total	

Remarks :

Applications

Available Sizes

Confirmed by :
KAM CERAMICS

Date :