



# KAM CERAMICS

## INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **BALL CLAY**

Code : **K.C.BA-JKF004**

Technical Properties	
M.O.R. ( Kg/Cm <sup>2</sup> )	*
Plasticity ( Peff. )	*
Firing Whiteness ( 1180 °C )	*
Firing Shrinkage ( 1180 °C )	*
Physial Form	*
Packing	*

Mineral Composition	

Chemical analysis	
SiO <sub>2</sub>	69.25
Al <sub>2</sub> O <sub>3</sub>	19.02
Na <sub>2</sub> O	0.89
K <sub>2</sub> O	3.72
MgO	0.40
CaO	0.03
Fe <sub>2</sub> O <sub>3</sub>	0.50
TiO <sub>2</sub>	0.85
MnO	0.01
P <sub>2</sub> O <sub>5</sub>	*
SO <sub>3</sub>	*
L.O.I.	4.81
Total	

Remarks :

Applications

Available Sizes

Confirmed by :  
KAM CERAMICS

Date :