



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **BALL CLAY**

Code : **K.C.BA-
JKF006**

Technical Properties	
M.O.R. (Kg/Cm ²)	*
Plasticity (Peff.)	*
Firing Whiteness (1180 °C)	*
Firing Shrinkage (1180 °C)	*
Physial Form	*
Packing	*

Mineral Composition	

Chemical analysis	
SiO ₂	64.63
Al ₂ O ₃	18.12
Na ₂ O	0.86
K ₂ O	3.69
MgO	0.36
CaO	0.13
Fe ₂ O ₃	3.26
TiO ₂	0.79
MnO	0.0
P ₂ O ₅	*
SO ₃	*
L.O.I.	7.78
Total	

Remarks :

Applications

Avallable Sizes

Confirmed by :
KAM CERAMICS

Date :