



# KAM CERAMICS

## INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Ballclay**

Code : **K.C.BA-TW2002**

Technical Properties	
M.O.R. ( Kgf/Cm <sup>2</sup> )	
Plasticity	
Firing Whiteness ( at .... °C )	
Firing Shrinkage ( at .... °C )	
Physial Form	
Packing	

Mineral Composition	

Chemical analysis	
SiO <sub>2</sub>	64.11
Al <sub>2</sub> O <sub>3</sub>	21.25
Na <sub>2</sub> O	0.50
K <sub>2</sub> O	4.07
MgO	0.51
CaO	0.10
Fe <sub>2</sub> O <sub>3</sub>	1.15
TiO <sub>2</sub>	0.65
MnO	0.01
P <sub>2</sub> O <sub>5</sub>	0.07
SO <sub>3</sub>	1.98
L.O.I.	5.46
Total	99.86

Confirmed by :  
KAM CERAMICS

Date :