



# KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **BENTONITE**

Code : **K.C.BE-153**

Technical Properties	
Fired M.O.R. ( Kgf/Cm <sup>2</sup> )	*
Moisture (%)	*
Fired color	*
Shrinkage (%)	*
Water Absorption (%)	*
L,a,b values	*

Mineral Composition	
	*
	*
	*
	*
	*

Chemical analysis	
SiO <sub>2</sub>	61.62
Al <sub>2</sub> O <sub>3</sub>	12.61
Na <sub>2</sub> O	2.23
K <sub>2</sub> O	1.71
MgO	2.8
CaO	2.1
Fet	2.32
TiO <sub>2</sub>	0.43
MnO	0.05
P <sub>2</sub> O <sub>5</sub>	0.07
SO <sub>3</sub>	0.13
L.O.I.	12.94
Total	*

Remarks :

Applications

Available Sizes

Confirmed by :  
KAM CERAMICS

Date :