



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

BENTONITE

Code :

K.C.BE-188

Physical Analysis	
Percent of Montmorillonite	*
Percent Of Montmorillonite mn 619	*
Gelling index after 8 hours	*
Gelling index after 24 hours	*
Gelling index after 2 hours	*
Percent of Moisture	*
YP/PV	*
Yield Point	*
PH	*
Wet Tensile Strength (kgF/cm2)	*
Green Compressive Strength (KgF/cm2)	*
Yield	*
Water Absorption Percent	374
P%	0.016

Chemical analysis	
SiO2	44.96
Al2O3	6.71
Na2O	*
K2O	1.50
MgO	1.21
CaO	1.95
Fe2O3	*
TiO2	0.157
MnO	0.035
P2O5	0.003
SO3	*
L.O.I.	*
Total	*

Remarks :	
Applications	Available Sizes

Confirmed by :
KAM CERAMICS

Date :