



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Feldspathoid**

Code : **K.C.FE-001**

Technical Properties	
M.O.R. (Kg/Cm ²)	15 - 20
Plasticity (Peff.)	*
Firing Whiteness (1180 °C)	Dark Cream
Firing Shrinkage (1180 °C)	8.50
Physial Form	Lump
Packing	Bulk

Mineral Composition	
Quartz	Kaolinite
Feldspar	Calcite

Chemical analysis	
SiO ₂	74.09
Al ₂ O ₃	16.44
Na ₂ O	0.85
K ₂ O	3.97
MgO	0.56
CaO	0.39
Fe ₂ O ₃	0.47
TiO ₂	0.26
MnO	0.01
P ₂ O ₅	0.10
SO ₃	0.01
L.O.I.	2.77
Total	99.92

Confirmed by :
KAM CERAMICS

Date :