



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Feldspathoid**

Code : **K.C.FE-002**

Technical Properties	
M.O.R. (Kg/Cm ²)	15 - 20
Plasticity (Peff.)	*
Firing Whiteness (1180 °C)	Dark Cream
Firing Shrinkage (1180 °C)	8.5
Physial Form	Lump
Packing	Bulk

Mineral Composition	
Quartz	Kaolinite
Feldspar	Calcite

Chemical analysis	
SiO ₂	72 ± 1
Al ₂ O ₃	15 ± 0.5
Na ₂ O	3 ± 0.5
K ₂ O	2 ± 0.2
MgO	0.7 ± 0.2
CaO	2.5 ± 0.5
Fe ₂ O ₃	0.7 ± 0.1
TiO ₂	0.25
MnO	*
P ₂ O ₅	*
SO ₃	*
L.O.I.	4 ± 0.5
Total	***

Remarks :

Applications

Tile - Body

Available Sizes

< 40 cm

Confirmed by :
KAM CERAMICS

Date :