



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **SODIC POTASH
FELDSPAR**

Code : **K.C.FE-151**

Technical Properties	
Fired M.O.R. (Kg/Cm ²)	
Moisture (%)	
Fired color	
Shrinkage (%)	
Water Absorption (%)	
L,a,b values	

Mineral Composition	

Chemical analysis	
SiO ₂	73.01
Al ₂ O ₃	12.39
Na ₂ O	4.61
K ₂ O	2.78
MgO	0.29
CaO	1.90
Fe ₂ O ₃	1.21
TiO ₂	0.084
MnO	0.019
P ₂ O ₅	0.025
SO ₃	0.721
L.O.I.	2.82
Total	

Remarks :	
Applications	Available Sizes

Confirmed by :
KAM CERAMICS

Date :