



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

**SODIC POTASIC
FELDSPAR**

Code : K.C.FE-152

Technical Properties	
Fired M.O.R. (Kg/Cm ²)	
Moisture (%)	
Fired color	
Shrinkage (%)	
Water Absorption (%)	
L,a,b values	

Mineral Composition	

Chemical analysis	
SiO ₂	69.23
Al ₂ O ₃	14.32
Na ₂ O	6.22
K ₂ O	1.78
MgO	1.56
CaO	1.14
Fe ₂ O ₃	3.29
TiO ₂	0.451
MnO	0.022
P ₂ O ₅	0.127
SO ₃	0.019
L.O.I.	1.55
Total	

Remarks :

Applications

Available Sizes

Confirmed by :
KAM CERAMICS

Date :