



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **SODIC
POTASH
FELDSPAR**

Code : **K.C.FE-155**

Technical Properties	
Fired M.O.R. (Kgf/Cm ²)	
Moisture (%)	
Fired color	
Shrinkage (%)	
Water Absorption (%)	
L,a,b values	

Mineral Composition	

Chemical analysis	
SiO ₂	76.25
Al ₂ O ₃	13.56
Na ₂ O	3.35
K ₂ O	5.28
MgO	0.05
CaO	0.44
Fe ₂ O ₃	0.60
TiO ₂	0.01
MnO	0.01
P ₂ O ₅	0.03
SO ₃	0.01
L.O.I.	1.3
Total	*

Remarks :	
Applications	Available Sizes

Confirmed by :
KAM CERAMICS

Date :