



# KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

**SODIC POTASH  
FELDSPAR**

Code : K.C.FE-157

Technical Properties	
Fired M.O.R. ( Kgf/Cm <sup>2</sup> )	
Moisture (%)	
Fired color	
Shrinkage (%)	
Water Absorption (%)	
L,a,b values	

Mineral Composition	

Chemical analysis	
SiO <sub>2</sub>	74.68
Al <sub>2</sub> O <sub>3</sub>	14.33
Na <sub>2</sub> O	4.34
K <sub>2</sub> O	4.62
MgO	0.13
CaO	0.51
Fe <sub>2</sub> O <sub>3</sub>	0.47
TiO <sub>2</sub>	<0.01
MnO	<0.01
P <sub>2</sub> O <sub>5</sub>	0.29
S	<0.01
L.O.I.	0.39
Total	*

Remarks :

Applications

Available Sizes

Confirmed by :  
KAM CERAMICS

Date :