



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

**SODIC POTASH
FELDSPAR**

Code : K.C.FE-158

Technical Properties	
Fired M.O.R. (Kgf/Cm ²)	
Moisture (%)	
Fired color	
Shrinkage (%)	
Water Absorption (%)	
L,a,b values	

Mineral Composition	

Chemical analysis	
SiO ₂	74.15
Al ₂ O ₃	14.61
Na ₂ O	3.51
K ₂ O	5.32
MgO	0.15
CaO	0.94
Fe ₂ O ₃	0.22
TiO ₂	0.03
MnO	0.01
P ₂ O ₅	0.35
S	<0.01
L.O.I.	0.96
Total	*

Remarks :

Applications

Available Sizes

Confirmed by :
KAM CERAMICS

Date :