



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

**SODIC POTASH
FELDSPAR**

Code : K.C.FE-159

Technical Properties	
Fired M.O.R. (Kgf/Cm ²)	
Moisture (%) @110C	0.18
Fired color	Off-white
Shrinkage (%)	
Water Absorption (%)	
L,a,b values	

Mineral Composition	

Chemical analysis	
SiO ₂	76.88
Al ₂ O ₃	13.22
Na ₂ O	4.53
K ₂ O	1.45
MgO	0.27
CaO	0.75
Fe ₂ O ₃	0.22
TiO ₂	0.22
MnO	<0.01
P ₂ O ₅	*
S	*
L.O.I.	1.83
Total	*

Remarks :

Applications

Available Sizes

Confirmed by :
KAM CERAMICS

Date :