



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

**Sodic POTASIC
FELDSPAR**

Code : **K.C.FE-EB001**

Technical Properties	
Fired M.O.R. (Kg/Cm ²)	*
Moisture (%)	0.13
Fired color	Creamish
Shrinkage (%)	11.84
Water Absorption (%)	0.04
L,a,b values	68.47,1.66,9.05

Mineral Composition	

Chemical analysis	
SiO ₂	75.79
Al ₂ O ₃	13.75
Na ₂ O	3.81
K ₂ O	3.63
MgO	0.59
CaO	0.54
Fe ₂ O ₃	0.44
TiO ₂	0.13
MnO	*
P ₂ O ₅	*
SO ₃	*
L.O.I.	1.32
Total	

Remarks :

Applications

Available Sizes

Confirmed by :
KAM CERAMICS

Date :