



# KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Feldspar**

Code : **K.C.FE-GH001**

| Technical Properties           |   |
|--------------------------------|---|
| M.O.R. ( Kgf/Cm <sup>2</sup> ) | * |
| Plasticity ( Peff. )           | * |
| Firing Whiteness ( 1180 °C )   | * |
| Firing Shrinkage ( 1180 °C )   | * |
| Physial Form                   | * |
| Packing                        | * |

| Mineral Composition |  |
|---------------------|--|
|                     |  |
|                     |  |
|                     |  |
|                     |  |
|                     |  |

| Chemical analysis              |       |
|--------------------------------|-------|
| SiO <sub>2</sub>               | 74.21 |
| Al <sub>2</sub> O <sub>3</sub> | 14.41 |
| Na <sub>2</sub> O              | 3.98  |
| K <sub>2</sub> O               | 5.83  |
| MgO                            | 0.15  |
| CaO                            | 0.65  |
| Fe <sub>2</sub> O <sub>3</sub> | 0.25  |
| TiO <sub>2</sub>               | 0.08  |
| MnO                            | *     |
| P <sub>2</sub> O <sub>5</sub>  | *     |
| SO <sub>3</sub>                | *     |
| L.O.I.                         | 0.68  |
| Total                          | *     |

Remarks :

Applications

Avallable Sizes

Confirmed by :  
**KAM CERAMICS**

Date :