



# KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

**Potassium  
feldspar**

Code : **K.C.FK-110**

Technical Properties	
M.O.R. ( Kg/Cm <sup>2</sup> )	*
Plasticity ( Peff. )	*
Firing Whiteness ( 1180 °C )	*
Firing Shrinkage ( 1180 °C )	*
Physial Form	*
Packing	*

PHYSICAL PROPERTIES	
Swelling Factor (ml/2g)	
Gellation Factor	
Montmorilonite	
Sintering point	

Chemical analysis	
SiO <sub>2</sub>	70.98
Al <sub>2</sub> O <sub>3</sub>	16.54
Na <sub>2</sub> O	1.49
K <sub>2</sub> O	9.96
MgO	0.07
CaO	0.26
Fe <sub>2</sub> O <sub>3</sub>	0.36
TiO <sub>2</sub>	0.155
MnO	0.002
P <sub>2</sub> O <sub>5</sub>	0.004
S	0.002
L.O.I.	0.05
Total	

Remarks :

Applications

Available Sizes

Confirmed by :  
KAM CERAMICS

Date :