



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : POTASH FELDSPAR

Code : K.C.FK-164

Technical Properties	
Fired M.O.R. (Kgf/Cm ²)	*
Moisture (%)	0.05
Fired color	*
Shrinkage (%)	*
Water Absorption (%)	*
L,a,b values	93.89,1.25,3.56

Mineral Composition	
Free Iron (ppm)	185
Fusion (%)	5.45
Acid Test in 20% HCL	Low Effervescence

Chemical analysis	
SiO ₂	71.45
Al ₂ O ₃	13.48
Na ₂ O	1.00
K ₂ O	10.40
MgO	0.13
CaO	1.36
Fe ₂ O ₃	0.06
TiO ₂	0.59
MnO	*
P ₂ O ₅	*
SO ₃	*
L.O.I.	1.53
Total	

Remarks :	
Applications	Available Sizes

Confirmed by :
KAM CERAMICS

Date :