



# KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Feldspar**

Code : **K.C.FK-GH002**

Technical Properties	
M.O.R. ( Kg/Cm <sup>2</sup> )	*
Plasticity ( Peff. )	*
Firing Whiteness ( 1180 °C )	*
Firing Shrinkage ( 1180 °C )	*
Physial Form	*
Packing	*

Mineral Composition	

Chemical analysis	
SiO <sub>2</sub>	66.65
Al <sub>2</sub> O <sub>3</sub>	18.81
Na <sub>2</sub> O	2.60
K <sub>2</sub> O	10.96
MgO	0.01
CaO	0.35
Fe <sub>2</sub> O <sub>3</sub>	0.10
TiO <sub>2</sub>	*
MnO	0.009
P <sub>2</sub> O <sub>5</sub>	0.07
SO <sub>3</sub>	*
L.O.I.	0.43
Total	

Remarks :

Applications

Avallable Sizes

Confirmed by :  
**KAM CERAMICS**

Date :