



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Feldspar**

Code : **K.C.FK-H001**

Technical Properties	
M.O.R. (Kgf/Cm ²)	*
Plasticity (Peff.)	*
Firing Whiteness (1180 °C)	*
Firing Shrinkage (1180 °C)	*
Physial Form	*
Packing	*

Mineral Composition	

Chemical analysis	
SiO ₂	65.82
Al ₂ O ₃	16.12
Na ₂ O	1.60
K ₂ O	13.89
MgO	0.00
CaO	0.48
Fe ₂ O ₃	0.21
TiO ₂	0.00
MnO	*
P ₂ O ₅	0.34
SO ₃	0.00
L.O.I.	0.42
Total	

Remarks :

Applications

Avallable Sizes

Confirmed by :
KAM CERAMICS

Date :