



# KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Sodic Fedspar**

Code : **K.C.FN-001**

Technical Properties	
M.O.R. ( Kg/Cm <sup>2</sup> )	***
Plasticity	
Firing Whiteness	
Firing Shrinkage ( at .... °C )	
Physial Form	
Packing	

Mineral Composition	

Chemical analysis	
SiO <sub>2</sub>	74.60
Al <sub>2</sub> O <sub>3</sub>	15.50
Na <sub>2</sub> O	8.07
K <sub>2</sub> O	0.50
MgO	0.09
CaO	0.23
Fe <sub>2</sub> O <sub>3</sub>	0.53
TiO <sub>2</sub>	0.03
MnO	< 0.01
P <sub>2</sub> O <sub>5</sub>	0.02
SO <sub>3</sub>	< 0.02
L.O.I.	0.48
Total	100.05

Confirmed by :  
**KAM CERAMICS**

Date :