



# KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Sodic Fedspar**

Code : **K.C.FN-002**

Technical Properties	
M.O.R. ( Kgf/Cm <sup>2</sup> )	***
Plasticity	
Firing Whiteness	
Firing Shrinkage ( at .... °C )	
Physial Form	
Packing	

Mineral Composition	

Chemical analysis	
SiO <sub>2</sub>	74.32
Al <sub>2</sub> O <sub>3</sub>	15.30
Na <sub>2</sub> O	7.73
K <sub>2</sub> O	0.24
MgO	0.07
CaO	0.37
Fe <sub>2</sub> O <sub>3</sub>	0.28
TiO <sub>2</sub>	0.20
MnO	0.01
P <sub>2</sub> O <sub>5</sub>	0.05
SO <sub>3</sub>	0.01
L.O.I.	1.43
Total	100.01

Confirmed by :  
KAM CERAMICS

Date :