



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Sodium Feldspar**

Code : **K.C.FN-003**

Technical Properties	
M.O.R. (Kg/Cm ²)	*
Plasticity (Peff.)	*
Firing Whiteness (1180 °C)	White
Firing Shrinkage (1180 °C)	*
Physial Form	Crushed
Packing	Big Bag & Bulk

Mineral Composition	
Quartz	Kaolinite
Feldspar	Calcite

Chemical analysis	
SiO ₂	68 - 72
Al ₂ O ₃	15 - 17
Na ₂ O	7 - 8.5
K ₂ O	0.2 - 0.5
MgO	0.20
CaO	1.5 - 3
Fe ₂ O ₃	0.20 - 0.35
TiO ₂	0.10
MnO	*
P ₂ O ₅	*
SO ₃	*
L.O.I.	2 - 3
Total	***

Remarks :

Applications	Available Sizes
Table Ware - Body	< 40 cm
Tile - Body	< 5 mm
Glass	< 3 mm
	(200 - 250) μ

Confirmed by :
KAM CERAMICS

Date :