



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Sodic FELDSPAR**

Code : **K.C.FN-105**

Technical Properties	
Fired M.O.R. (Kg/Cm ²)	*
Moisture (%)	0.08
Fired color	Creamish
Shrinkage (%)	13.10
Water Absorption (%)	0.05
L,a,b values	71.18,1.44,7.15

Mineral Composition	

Chemical analysis	
SiO ₂	77.21
Al ₂ O ₃	14.20
Na ₂ O	7.67
K ₂ O	0.05
MgO	0.04
CaO	0.20
Fe ₂ O ₃	0.16
TiO ₂	0.07
MnO	
P ₂ O ₅	
SO ₃	
L.O.I.	0.40
Total	

Remarks :	Applications	Available Sizes

Confirmed by :
KAM CERAMICS

Date :