



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **sodic feldspar**

Code : **K.C.FN-106**

Technical Properties	
Fired M.O.R. (Kg/Cm ²)	*
Moisture (%)	0.09
Fired color	White
Shrinkage (%)	13.70
Water Absorption (%)	0.04
L,a,b values	68.910,1.92,10.53

Mineral Composition	

Chemical analysis	
SiO ₂	78.28
Al ₂ O ₃	13.52
Na ₂ O	4.24
K ₂ O	1.63
MgO	0.51
CaO	0.97
Fe ₂ O ₃	0.30
TiO ₂	0.10
MnO	
P ₂ O ₅	
S	
L.O.I.	0.42
Total	

Remarks :	
Applications	Available Sizes

Confirmed by :
KAM CERAMICS

Date :