



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com


Type : **SODIC FELDSPAR**

Code : **K.C.FN-154**

Technical Properties	
Fired M.O.R. (Kg/Cm ²)	90
Dry M.O.R. (Kg/Cm ²)	0
Moisture (%)	<2
Shrinkage (%)	1.7
Water Absorption (%)	*
L,a,b values	*

Chemical analysis	
SiO ₂	65
Al ₂ O ₃	20
Na ₂ O	7- 8
K ₂ O	0.8
MgO	0.5
CaO	3.6
Fe ₂ O ₃	0.3
TiO ₂	0.6
MnO	*
P ₂ O ₅	*
SO ₃	0.05
L.O.I.	1.3
Total	

Technical Properties	
D	1.63
V	14"
R	0.8
LOI	1.5
A. H ₂ O	14.7
KILN.C	60
KILN.T°C	1178



Confirmed by :
KAM CERAMICS

Date :