



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

Sodic FELDSPAR

Code : K.C.FK-ST2000

Technical Properties	
Fired M.O.R. (Kgf/Cm ²)	*
Moisture (%) @ 1000°C	0.16
Fired color	*
Shrinkage (%)	*
Water Absorption (%)	*
L,a,b values	*

Mineral Composition	
Free Iron (ppm)	*
Fusion (%)	*
Acid Test in 20% HCL	*

Chemical analysis	
SiO ₂	71.80
Al ₂ O ₃	14.48
Na ₂ O	8.76
K ₂ O	0.24
MgO	0.26
CaO	1.45
Fe ₂ O ₃	0.52
TiO ₂	0.19
MnO	<0.01
P ₂ O ₅	*
SO ₃	*
L.O.I.	1.52
Total	

Remarks :

Applications

Available Sizes

Confirmed by :
KAM CERAMICS

Date :