



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

**SODIC
Feldspar**

Code : **K.C.FN-165**

Technical Properties	
M.O.R. (Kgf/Cm ²)	*
Plasticity (Peff.)	*
Firing Whiteness (1180 °C)	*
Firing Shrinkage (1180 °C)	*
Physial Form	*
Packing	*

Mineral Composition	

Chemical analysis	
SiO ₂	76.64
Al ₂ O ₃	12.33
Na ₂ O	6.72
K ₂ O	0.36
MgO	0.46
CaO	1.96
Fe ₂ O ₃	0.79
TiO ₂	0.04
MnO	0.01
P ₂ O ₅	0.01
SO ₃	<0.1
L.O.I.	0.99
Total	*

Remarks :

Applications

Available Sizes

Confirmed by :
KAM CERAMICS

Date :