



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type: Sodium Feldspar

Code : K.C.FN-323

Technical Properties	
Fired M.O.R (kg/cm2)	*
Dry Strength(kg/cm2)	*
Water Absorption (%)	*
specific gravity	*
Fired Shrinkage (%)	*
whiteness (%)	*

Technical Properties	
Fired Shrinkage (%)	*
Water Absorption (%)	*
Fired M.O.R (kg/cm2)	*
Viscosity "	*
L.O.I (%)	*

Chemical analysis	
SiO2	78.22
Al2O3	13.19
Na2O	7.54
K2O	0.08
MgO	0.12
CaO	0.29
Fe2O3	0.22
TiO2	<0.01
Mno	<0.01
S	<0.02
L.O.I	<0.01
Cl	*
total	*

**Confirmed by :
KAM CERAMICS**

Date :