



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : Sodic Feldspar

Code : K.C.FN-355

Technical Properties	
Fired M.O.R. (Kgf/Cm ²)	*
Moisture (%) @ 110°C	0.26
Fired color	Light Creamish white
L,a,b values	78.6,1.4,7.6

Mineral Composition	
Free Iron (ppm)	*
sampleFusion	medium
Acid Test in 20% HCL	A
Sample Firing Temperature / Cycle time	
1200°C, 60 min Cycle Lab Roller Kiln	

Chemical analysis	
SiO ₂	76.38
Al ₂ O ₃	13.26
Na ₂ O	7.15
K ₂ O	0.24
MgO	0.20
CaO	0.75
Fe ₂ O ₃	0.27
TiO ₂	0.19
MnO	<0.01
P ₂ O ₅	*
SO ₃	*
L.O.I at 110 °C	0.26
Total	*

Confirmed by :
KAM CERAMICS

Date :