



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : Sodic feldspar

Code : K.C.FN-356

Technical Properties	
Fired M.O.R. (Kg/Cm ²)	*
Moisture (%) @ 110°C	*
Fired color	*
L,a,b values	*

Mineral Composition	
Free Iron (ppm)	*
sampleFusion	*
Acid Test in 20% HCL	*
Sample Firing Temperature / Cycle time	
1200°C, 60 min Cycle Lab Roller Kiln	

Chemical analysis	
SiO ₂	70.13
Al ₂ O ₃	18.12
Na ₂ O	10.71
K ₂ O	0.13
MgO	<0.05
CaO	0.34
Fe ₂ O ₃	0.14
TiO ₂	0.20
MnO	<0.05
P ₂ O ₅	<0.05
SO ₃	<0.05
L.O.I	0.23
Total	

Confirmed by :

Date :

KAM CERAMICS