



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Sodic feldspar**

Code : **K.C.FN-JKF002**

Technical Properties	
M.O.R. (Kg/Cm ²)	*
Plasticity (Peff.)	*
Firing Whiteness (1180 °C)	*
Firing Shrinkage (1180 °C)	*
Physial Form	*
Packing	*

Mineral Composition	

Chemical analysis	
SiO ₂	70.06
Al ₂ O ₃	17.96
Na ₂ O	9.49
K ₂ O	0.19
MgO	0.0
CaO	0.99
Fe ₂ O ₃	0.42
TiO ₂	0.37
MnO	0.0
P ₂ O ₅	*
S	*
L.O.I.	0.21
Total	

Remarks :

Applications

Avallable Sizes

Confirmed by :
KAM CERAMICS

Date :