



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Feldspar Sodic**

Code : **K.C.FN-ZKH**

| Technical Properties | |
|--------------------------------|---|
| M.O.R. (Kgf/Cm ²) | * |
| Plasticity (Peff.) | * |
| Firing Whiteness (1180 °C) | * |
| Firing Shrinkage (1180 °C) | * |
| Physial Form | * |
| Packing | * |

| Mineral Composition | |
|---------------------|--|
| Quartz | |
| Feldspar | |
| | |
| | |
| | |

| Chemical analysis | |
|--------------------------------|--------|
| SiO ₂ | 79.04 |
| Al ₂ O ₃ | 12.99 |
| Na ₂ O | 6.83 |
| K ₂ O | 0.14 |
| MgO | 0.07 |
| CaO | 0.38 |
| Fe ₂ O ₃ | 0.11 |
| TiO ₂ | 0.03 |
| MnO | <0.01 |
| P ₂ O ₅ | 0.07 |
| S | <0.02 |
| L.O.I. | 0.40 |
| Total | 100.06 |

Remarks :

Confirmed by :
KAM CERAMICS

Date :