



# KAM CERAMICS

## INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Kaolin**

Code : **K.C.KA-007**

Technical Properties	
M.O.R. ( Kgf/Cm <sup>2</sup> )	
Plasticity	
Firing Whiteness	
Firing Shrinkage ( at .... °C )	
Physial Form	
Packing	

Mineral Composition	

Chemical analysis	
SiO <sub>2</sub>	74.40
Al <sub>2</sub> O <sub>3</sub>	14.10
Na <sub>2</sub> O	1.99
K <sub>2</sub> O	0.61
MgO	2.13
CaO	0.93
Fe <sub>2</sub> O <sub>3</sub>	0.70
TiO <sub>2</sub>	0.23
MnO	*
P <sub>2</sub> O <sub>5</sub>	*
SO <sub>3</sub>	*
L.O.I.	4.75
Total	99.84

Confirmed by :  
**KAM CERAMICS**

Date :