



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **KAOLIN**

Code : **K.C.KA-019**

Technical Properties	
M.O.R. (Kgf/Cm ²)	
Plasticity (Peff.)	
Firing Whiteness (1180 °C)	
Firing Shrinkage (1180 °C)	
Physial Form	
Packing	

Mineral Composition	

Chemical analysis	
SiO ₂	66.30
Al ₂ O ₃	21.28
Na ₂ O	1.65
K ₂ O	1.38
MgO	0.55
CaO	0.49
Fe ₂ O ₃	2.30
TiO ₂	***
MnO	***
P ₂ O ₅	***
SO ₃	0.58
L.O.I.	5.27
Total	99.80

Confirmed by :
KAM CERAMICS

Date :