



# KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **KAOLIN**

Code : **K.C.KA-023**

Technical Properties	
Green M.O.R. ( Kg/Cm <sup>2</sup> )	***
Dried M.O.R. ( Kg/Cm <sup>2</sup> )	18.09
Firing Shrinkage ( 1190 °C )	0.12
Firing STRENGTH ( 1190 °C )	459
WATER ABSORPTION	0.06
Packing	BULK & BIG BAG

Mineral Composition	

Chemical analysis	
SiO <sub>2</sub>	70.60
Al <sub>2</sub> O <sub>3</sub>	18.01
Na <sub>2</sub> O	0.43
K <sub>2</sub> O	2.15
MgO	0.50
CaO	0.14
Fe <sub>2</sub> O <sub>3</sub>	0.78
TiO <sub>2</sub>	0.08
MnO	0.00
P <sub>2</sub> O <sub>5</sub>	0.00
SO <sub>3</sub>	0.56
L.O.I.	5.76
Total	***

Confirmed by :  
**KAM CERAMICS**

Date :