



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : KAOLIN

Code : K.C.KA-MKCC

Technical Properties	
M.O.R. (Kg/Cm ²)	21 ± 2
Plasticity (Peff.)	29 ±1
Firing Whiteness (1180 °C)	80 ± 2
Firing Shrinkage (1200°C)	14 ± 1
Physial Form	***
Packing	***

Mineral Composition	

Chemical analysis	
SiO ₂	63 ± 1
Al ₂ O ₃	25± 1
Na ₂ O	<0.2
K ₂ O	3 ± 0.5
MgO	<0.15
CaO	<0.5
Fe ₂ O ₃	<0.3
TiO ₂	<0.2
MnO	*
P ₂ O ₅	*
SO ₃	Trace
L.O.I.	6 ± 1
Total	***

Confirmed by :
KAM CERAMICS

Date :