



# KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

KAOLIN

Code :

K.C.KA-  
QCH007

Technical Properties	
M.O.R. ( Kgf/Cm <sup>2</sup> )	*
Plasticity ( Peff. )	*
Firing Whiteness ( 1180 °C )	*
Firing Shrinkage ( 1180 °C )	*
Physial Form	*
Moisture @ 110	0.84

Mineral Composition	

Chemical analysis	
SiO <sub>2</sub>	72.41
Al <sub>2</sub> O <sub>3</sub>	19.36
Na <sub>2</sub> O	0.5
K <sub>2</sub> O	0.30
MgO	0.27
CaO	0.75
Fe <sub>2</sub> O <sub>3</sub>	0.35
TiO <sub>2</sub>	0.40
MnO	*
P <sub>2</sub> O <sub>5</sub>	*
SO <sub>3</sub>	*
L.O.I.	4.75
Total	

Remarks :

Applications

Available Sizes

Confirmed by :  
KAM CERAMICS

Date :