



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type: **KAOLIN**

Code: **K.C.KA-SJ2**

Technical Properties	
M.O.R. (Kgf/Cm ²)	
Plasticity (Peff.)	
Firing Whiteness (1180 °C)	
Firing Shrinkage (1180 °C)	
Physial Form	
Packing	

Mineral Composition	

Chemical analysis	
SiO ₂	64.33
Al ₂ O ₃	16.88
Na ₂ O	1.93
K ₂ O	1.35
MgO	0.15
CaO	2.00
Fe ₂ O ₃	1.55
TiO ₂	0.25
MnO	<0.01
P ₂ O ₅	0.17
S	1.20
L.O.I.	9.10
Total	98.91

Confirmed by :
KAM CERAMICS

Date :