



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

KAOLIN
FELDSPAR

Code : K.C.KAFK-135

Technical Properties	
Fired M.O.R. (Kg/Cm ²)	
Water of Plasticity (%)	
Fired color	
Shrinkage (%)	
Water Absorption (%)	
L,a,b values	

Mineral Composition	
Dry M.O.R. (Kg/Cm ²)	
Green M.O.R. (Kg/Cm ²)	
Moisture (%)	
Acide test (@20%HCL)	

Chemical analysis	
SiO ₂	73.54
Al ₂ O ₃	14.06
Na ₂ O	0.29
K ₂ O	2.68
MgO	0.41
CaO	2.21
Fe ₂ O ₃	0.65
TiO ₂	0.09
MnO	0.07
P ₂ O ₅	0.03
SO ₃	0.06
L.O.I.	5.55
Total	

Remarks :	
Applications	Available Sizes

Confirmed by :
KAM CERAMICS

Date :