



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

TALC

Code : K.C.TA-171

Technical Properties	
M.O.R. (Kgf/Cm ²)	*
Plasticity (Peff.)	*
Firing Whiteness (1180 °C)	*
Firing Shrinkage (1180 °C)	*
Physial Form	*
Packing	*

Mineral Composition	

Chemical analysis	
SiO ₂	39.64
Al ₂ O ₃	28.57
Na ₂ O	0.34
K ₂ O	5.28
MgO	14.45
CaO	0.19
Fe ₂ O ₃	3.28
TiO ₂	0.32
MnO	0.03
P ₂ O ₅	0.09
SO ₃	<0.02
L.O.I	7.96
total	*

Remarks :

Applications

Available Sizes

Confirmed by :
KAM CERAMICS

Date :