



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type:TALC

Code : K.C.TA-272

Technical Properties / 1135°C (43min)	
Fired M.O.R (kg/cm2)	*
Dry Strength(kg/cm2)	*
Water Absorption (%)	*
specific gravity	*
Fired Shrinkage (%)	*
whiteness (%)	*

Technical Properties / 1190°C (58min)	
Fired Shrinkage (%)	*
Water Absorption (%)	*
Fired M.O.R (kg/cm2)	*
Vicosity "	*
L.O.I (%)	*

Chemical analysis	
SiO2	52.10
Al2O3	1.00
Na	0.20
K	0.00
MgO	29.80
CaO	4.30
Fe2O3	0.16
TiO2	0.02
Mno	*
SO3	0.06
L.O.I	12.10
Cl	0.00
total	*

Producing Size
(White Talcium) 800 - 2500 Mesh

Confirmed by :

KAM CERAMICS

Date :