



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : TALC

Code : K.C.TA-NSH002

Technical Properties	
M.O.R. (Kgf/Cm ²)	*
Plasticity (Peff.)	*
Firing Whiteness (1180 °C)	*
Firing Shrinkage (1180 °C)	*
Physial Form	*
Packing	*

Mineral Composition	

Chemical analysis	
SiO ₂	42.5
Al ₂ O ₃	0.23
Cr ₂ O ₃	0.094
K ₂ O	0.0045
MgO	39.7
CaO	0.104
Fe ₂ O ₃	2.73
TiO ₂	0.0034
MnO	0.087
P ₂ O ₅	0.0048
SO ₃	0.15
L.O.I	13.93
total	*

Remarks :

Applications

Avallable Sizes

Confirmed by :
KAM CERAMICS

Date :